#### LASER INTERFEROMETER GRAVITATIONAL WAVE OBSERVATORY

# LIGO

### **COMPONENT SPECIFICATION**

E080133 -00- D

Drawing No Rev. Group

Sheet 1 of 2

### MIRROR BLANK MATERIAL, ALIGO PRE-MODE MATCHING TELESCOPE MIRROR #1

			APPROVALS		
AUTHOR:	CHECKED:	DATE	DCN NO.	REV	DATE
R. Martin, D. Reitze		04-01-08			

**Applicable Documents** 

D080159-00-D ALIGO Pre-Mode Matching Telescope Mirror #1 Blank

MIL-G-174-B Glass, Optical

Requirements

Physical Dimensions Per D080159-00-D ALIGO Pre-Mode Matching Telescope Mirror #1 Blank

Diameter 78 mm, +1 mm, -0 mm

Thickness 28 mm, +1 mm, -0 mm

Clear Aperture Central 70 mm

Serial Number Blanks shall be serialized as PMMT1-XX, where XX increments starting at 01

Material Fused Silica, Grade 0C

Final Shaping Shaping shall be performed using a progression of grit size ending with a 320 or smaller grit

wheel

Defect Depth Maximum on any surface or corner is less than 0.5 mm

Homogeneity  $\leq 2 \times 10^{-6}$  peak to valley at  $\lambda = 632.8$  nm, within the central 65 mm

Birefringence ≤ 1 nm/cm within the central 65 mm

Bubble and inclusion

cross section within

Given by the Grade 0C:

clear aperture  $Total \le 0.03 \text{ mm}^2/100 \text{ cm}^3 \text{ of glass}$ 

Inclusions with a diameter of 0.06 mm or less are disregarded

Maximum inclusion diameter ≤ 0.1 mm

Striae within the clear

aperture

Grade A according to MIL-G-174

Absorption < 20 ppm per centimeter at  $\lambda$ =1.06  $\mu$ m

# LIGO

### **COMPONENT SPECIFICATION**

E080133 -00- D

Drawing No Rev. Group

Sheet 2 of 2

## MIRROR BLANK MATERIAL, ALIGO PRE-MODE MATCHING TELESCOPE MIRROR #1

#### Table 1: Measurement Matrix - Frequency and Method

Specification	Test Method	Frequency of Inspection	Data Delivered	
Physical Dimensions	Visual Inspection	100%	Diameter, Thickness	
Serial Number	Visual Inspection	100%	Inspection Report included with Certification	
Material	Process Control Material Certification	100%	Certification	
Defect Depth	Visual Inspection	100%	Certification	
Homogeneity	Interferometric Measurement	100%	Certification	
Birefringence	MIL-G-174, Section 4.4.5	100%	Inspection Report included with Certification	
Inclusions	Visual Inspections	100%	Hand sketch indicating location, depth, and dimensions	
Striae	MIL-G-174, Section 4.4.5, method 1 or 2 (in optical axis only)	100%	Certification	
Absorption at 1.06 μm	Material Certification	100%	Certification	