



NOTES CONTINUED:

- 5. SCRIBE, ENGRAVE (A VIBRATORY TOOL MAY BE USED), LASER MARK OR MECHANICALLY STAMP (NO INKS OR DYES) DRAWING PART NUMBER, REVISION (AND VARIANT OR "TYPE" IF APPLICABLE) ON NOTED SURFACE OF PART FOLLOWED ON THE NEXT LINE WITH A THREE DIGIT SERIAL NUMBER. SERIAL NUMBERS START AT 001 FOR THE FIRST ARTICLE AND PROCEED CONSECUTIVELY. USE MINIMUM 0.12" HIGH CHARACTERS, UNLESS THE SIZE OF THE PART DICTATES SMALLER CHARACTERS. EXAMPLE: DXXXXXX-VY, TYPE-XX, S/N XXX
- 6. APPROXIMATE WEIGHT = X.XXX LB.
- 7. MACHINE ALL SURFACES TO REMOVE OXIDES AND MILL FINISH. USE OF ABRASIVE REMOVAL TECHNIQUES IS NOT ALLOWED. REFER TO LIGO-E0900364
- 8. ALL PARTS SHALL BE MANUFACTURED IN ACCORDANCE WITH LIGO SPECIFICATION E0900364.
- 9. ALL MATERIAL IS TO BE VIRGIN MATERIAL (i.e. NO WELD REPAIRS, PLUGS OR RECYCLED MATERIAL). NO REPAIRS SHALL BE MADE UNLESS APPROVED IN ADVANCE, AND IN WRITING, BY LIGO LABORATORY. REFER TO LIGO-E0900364.
- 10. SURFACE FINISH TO BE AS-PROCESSED FROM MILL/SUPPLIER, FREE FROM SCRATCHES OR GOUGES.
- 11. PART WILL BE PORCELAIN COATED PER LIGO SPECIFICATION E1000083 AFTER FABRICATION. THE INDICATED HOLES WILL BE MASKED PRIOR TO PORCELAIN COATING TO APPROXIMATELY 2.5-3X HOLE DIAMETER CENTERED ON BOTH SIDES OF THE HOLE.
- 12. DIMENSIONS APPLY BEFORE PORCELAIN COATING UNLESS SPECIFIED.
- 13. BEND RADIUS: UNLESS OTHERWISE NOTED, THE BEND RADIUS SHOULD BE THE MINIMUM REQUIRED TO FORM WITHOUT CRACKING OR REQUIRING ADDITIONAL WORK WHEN FORMING. IN PARTICULAR IF SHEET METAL IS TO BE PORCELAIN COATED, THE BEND RADIUS SHALL BE A MINIMUM OF .12" OUTSIDE RADIUS OF BEND UNLESS OTHERWISE NOTED.

| REV. | DATE | DCN # | DRAWING TREE # |
|------|-------------|----------|----------------|
| V1 | 20 MAY 2010 | E1000360 | E1000359 |
| - | - | - | - |
| - | - | - | - |



GENERAL VIEW
FOR REFERENCE ONLY
NO SCALE



| NOTES AND TOLERANCES: (UNLESS OTHERWISE SPECIFIED) | |
|--|---|
| DIMENSIONS ARE IN INCHES | 1. INTERPRET DRAWING PER ASME Y14.5-1994. |
| TOLERANCES: | 2. REMOVE ALL SHARP EDGES, .005-.015, FOR MACHINED PARTS. ROUND ALL EDGES APPROXIMATELY R.02 FOR SHEET METAL PARTS. |
| .XX ± .03 | 3. DO NOT SCALE FROM DRAWING. |
| .XXX ± .010 | 4. ALL MACHINING FLUIDS MUST BE FULLY SYNTHETIC, FULLY WATER SOLUBLE AND FREE OF SULFUR, SILICONE, AND CHLORINE. |
| ANGULAR ± 1.0° | |
| MATERIAL | 304, 316 OR 302 SSSL |
| FINISH | 63 μinch |

| | | | | | |
|---|---------------|------------|----------|----------------------------|-------------------------|
| CALIFORNIA INSTITUTE OF TECHNOLOGY MASSACHUSETTS INSTITUTE OF TECHNOLOGY | | PART NAME | | MANIFOLD-CRYO BAFFLE BRACE | |
| SYSTEM | ADVANCED LIGO | SUB-SYSTEM | AOS | DESIGNER | H. KELMAN 18 MAY 2010 |
| NEXT ASSY | D1001348 | CHECKER | M. SMITH | DRFTR | TQ. NGUYEN 12 SEPT 2010 |
| | | APPROVAL | D. COYNE | SIZE | DWG. NO. B D1000572 |
| | | | | SCALE | 1:2 |
| | | | | PROJECTION | |
| | | | | REV. | v1 |
| | | | | SHEET 1 OF 1 | |

D1000572_Manifold_Cryo_Baffle_Square_Brace, PART PDM REV: X-009, DRAWING PDM REV: X-004